TECHNICAL DATA SHEET

BW L 24 - Liquid Flux

EN 1045:2010 *FH 21*
AWS 5.31:2012

Standard Composition

Boron compounds - Trimethylborate

Technical Data

Working Temperature	
Density	0,852
Viscosity	n.d.
Colour	Transparent
Shelf life	6 Months
Flux residues	None

Applications

Flux BW 24 is a liquid flux with a high concentration (about 70%) that can only be used with vaporizers; the gas entering the vaporizers mechanically transports the liquid which, when burned in the flame, is able to locally produce a redox atmosphere. The advantages of this category of products are the cost-effectiveness of use, the absence or very low presence of residues (which are inert anyway), ease of application (it must not be spread or dosed) and resistance to heating. The BW 24 is mainly used in the metal furniture, refrigeration and air conditioning sectors.

Further Information

Flux is flammable. Read the safety data sheet before use.

Packaging

10 Lt, 25 Lt, 60 Lt, 200 Lt

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the f ield of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use f rom these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development. The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data s heets, specifications or drawings. Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply.

Sede Legale e Uffici
Via Friuli 5 | 20090 Fizzonasco di P.E. | Milano | Italy
TEL. +39 02 907 81 812 | FAX. +39 02 907 84 933
CF/P.IVA IT08049640967 | NUMERO REA: MI - 2000301
info@saldflux.com | saldflux@legalmail.it

Sede Magazzino
Via Privata Vico Veneto 32/5 | 20090 Fizzonasco di P.E. | Milano | Italy
Orari: 8.00 - 12.00 | 13.00 - 17.00

Stabilimento
Via Martiri Della Resistenza 6 | 20090 Fizzonasco di P.E. | Milano | Italy

TÜV SÜD ISO 9001