TECHNICAL DATA SHEET

TERNALLOY 491

Brazing alloys, Cadmium Free

EN ISO 17672:2016 -
AWS A5.8-92 -
ISO 3677:1997 B-Ag49CuZnMnNi-670/68(
DIN 8513
(EN 1044:1999)

Nominal Composition [%]

Ag	Cu	Zn	Sn	Si	Mn	Ni
49	27	21	-	-	2,5	0,5

Technical Data

Melting Point c.a. 670 - 690 °C
Working Temperature c.a. 690 °C
Density c.a. 9,0 gr/cm3
Tensile strength 250 - 300 Mpa
Elongation -
Electrycal Conductivity - m/? mm²
Operating temp. of brazed joint

Applications

TERNALLOY 491 MN is a low melting silver brazing alloy with excellent flow characteristics and high mechanical resistance. It is mainly employed for brazing of cemented carbides and materials difficult to wet such as tungsten, chromium, tantalum and titanium.
Typical applications are in tool industry. It can be used in brazing procedures by flame or induction. The suitable fluxes are F9 paste (suggested during a brazing process by induction) and F4 paste (suggested for all the otherapplications).

Suggested Flux

Base Metals

Steels, plain and alloyed. Also tungsten, molybdenum, tantalum and chromium; cemented

Heat Sources

Bare rods	Fluxcoated	Wire < Ø 1,0	Wire > Ø 1,0	Foil	Preforms	Paste
X	-	-	-	X	0	-

Our information about our products and equipment as well as our systems and procedures are based on comprehensive research and application technological experience. We communicate these results, but take no liability for respective single contracts that are exceeding thereof. We reserve the right to make technical changes in the process of product development in spoken and written terms to the best of our knowledge. Only as an exception do we give guarantees for appearance and workmanship or durability that has been specifically documented in an individual contract. Furthermore, our application technology services are available at your convenience for more detailed consultation such as the involvement in solving manufacturing and application technology problems. This does not however, release the user from their own responsibility for checking the input and recommendations we give for their own use prior to using that input or recommendation. This is especially applicable for foreign deliveries. This also applies to the trade mark rights of third parties, for applications and procedures that are not specifically given by us. In the event of damage or loss our liability is limited to indemnification of the same admeasurements as is foreseen in our general terms of sales and delivery in reference to deficiencies in quality.